

TecnoFib CROSS 230

REINFORCEMENT SYSTEMS WITH CARBON FIBRE FABRICS

Description Fabric of carbon macro-fibres, bi-directional, hot-welded warp, with very high tensile strength.

Advantages and characteristics The mechanical performance of the reinforcement system Tecnofib CROSS 230 shows a typical linear elastic behaviour till break. The tolerated static load applied, shall be 1/3 of the tensile strength of the fibre.

Fields of use **Together with the epoxy adhesive for impregnation TECNOEPO 701/UNIC in accordance with the Design Guidelines CNR - DT200/2004.**

Main applications:

- Restoration of vaults
- Reinforcement of water pipes and reservoirs.
- Recovery of structures with seismic damages.
- Restoration of masonry

Method of use The product is applied to the surface of the structural elements to be reinforced, by mean of epoxy adhesives (TECNOEPO 701 UNIC).

The installation of the fibre tissue with the adhesive can be made only after a thorough preparation of the substrate, using sand or grid-blasting, in order to remove all dust and incoherent parts. When the substrate is deteriorated or, in order to improve adhesion properties of the system, it is advisable to apply epoxy putty (TECNOEPO R) to level and repair the surface. The installation of the fabric has to start by the application by roller or brush of an epoxy primer, about 0,800 kg/m², on the internal contact substrate of the fibre.

Position the fibres, and roll with a special roller to release air and to allow the penetration of the resin into the fibre tissue. For consecutive layers, follow the same procedure, starting with the epoxy adhesive application. The curing depends on the reticulation time of the epoxy resin and it is linked to the climatic conditions like temperature and humidity. In particular, applications at temperature lower than +10°C, and at high relative humidity should be avoided. In case of application at temperatures below +10°C, and in order to have a pot life of the epoxy adhesive not too much delayed, it is advisable to heat slightly the environment.

Packaging Rolls of 100 linear meters, width 30 cm

Technical Characteristics (typical values)

- Principal mechanical characteristic: very high tensile strength.
- Tensile strength: > 4800 MPa
- Elasticity modulus at tensile strength: 240 GPa
- Elongation: 2,1 %
- Weight: 300 g/m²
- Fabric thickness: 0,166 mm
-

Safety indications Read carefully the safety indications on the packaging, or consult the relevant Material Safety Data Sheet of this product.

The above information is based on our best experiences and lab results and on results of the application of the product in various fields. Tecnochem Italiana is not responsible for negative performances due to not proper use of the product or for defects due to elements not connected with the quality of the product included wrong storage. Technical characteristic in this technical data sheet are up-to-dated periodically. Revision date of this technical data sheet is indicated below. Changes of this data sheet can be found in our web-site www.tecnochem.it where you can find the same technical data sheet updated in real time.

Emission date : 01/2006
Revision date : 10/2014

Nr rev. : 7

TECNOFIB CROSS 230
pag. 1/1

TECNOCHEM ITALIANA S.p.A.

24030 BARZANA (BERGAMO) ITALY – VIA SORTE 2/4,
TEL. **39 035 55.48.11 – TELEFAX **39 035 55.48.16
E-mail: info@tecnochem.it - www.tecnochem.it